

TECHNICAL INFORMATION



TECHNICAL INFORMATION RESIN AND CATALYST (Adhesive for EPDM and SBR)

| | |
|----------------------|---|
| COMPONENT | Isocyanate---liquid Polyurethane |
| PRESENTATION | Viscous / yellowish product |
| PACKING | Container 1000 Kg. / Bottle 220 Kg. |
| DESCRIPTION | Adhesive with viscous-yellowish component for layout adhesive. |
| TOXICITY AND ECOLOGY | Viscous product, avoid contact with skin. Do not inhale. Final product is not dangerous for health nor environment. |

CHEMICAL COMPOSITION

| MATERIAL | UNITY | VALUE |
|----------------------|-------|-----------------------------|
| DIISOCYANATE OF 4,4' | % | 25/30 |
| METHYLENEDIPHENY | % | according to law 67/548/CEE |
| ADHESIVE | % | |
| CATALYST | % | |

PHYSICAL PROPERTIES

| FEATURES | UNITY | VALUE |
|---------------|---------------------|----------------------|
| VISCOSITY | cps Brookfield 20°C | 300-500 |
| SOLID CONTENT | % | 100 without solvents |
| NCO CONTENT | % | 10+5 in weight |
| DENSITY | gr/cm3 | 1,2 |

HANDLING

Agglomerating and/or mixing machine
Wear gloves and avoid contact with the skin. Do not inhale.
Do not mix with water, alcohol, acids or amines.
Drying and hardening occur on 6-8 hours

CLEANING

Solvents and liquid detergents

STORAGE

Closed containers, in dry places and with temperatures under 30°C.
Stable for 6 months in closed original packages.
Not to use water fire extinguishers.